



**WESTERN BLENDED
PRODUCTS**
The Plasterer's Standard

Premium Acrylic Finish - Vera Mist

A 100% acrylic based interior & exterior decorative coating.



- 100% Acrylic Finish.
- Dirt Pickup Resistance Formula.
- Natural Color Aggregate.

Use for:



AFC Acrylic Finish Coats



Description:

Vera Mist is a stone mix that can be applied on both interior and exterior walls. Made up of differing colored quartz aggregates, this finish is packaged premixed to ensure a homogeneous natural stone look. Whether it's for an upscale exterior or a one of a kind interior look, Vera Mist is sure to enhance the look of every home. Vera Mist can be utilized in many different ways to complement other finishes in Western Blended Products systems. All Vera Mist textures may be troweled on by hand.

Packaging:

PAF Vera Mist is packaged is packaged in a 60 Lb (27.21 Kgs) pail.

Benefits and Use:

PAF Vera Mist is pre-mixed and ready to apply. PAF Vera Mist has excellent color retention and is also an extremely durable DPR architectural acrylic finish, which could be used in a variety of interior and exterior systems. Although PAF Vera Mist is recommended over Western 1-Kote exterior stucco systems previously prepared with BPS Super Fine Skim Coat, it can also be applied over properly prepared substrates such as masonry, concrete and other approved stucco systems.

Coverage:

PAF Vera Mist covers approximate 95 sq. ft. when applied at (1/8") one-eighth of an inch.

Preparation:

PAF Vera Mist must be applied over dry, clean surfaces, free of dust and imperfections. Basecoats receiving PAF Vera Mist shall be completely cured for a minimum of 24 hours prior to

application of PAF Vera Mist. If applied over concrete surfaces, concrete must be cured for a minimum of 28 days prior to application of PAF Vera Mist. All receiving substrates shall be coated with PAF Primer prior to PAF Vera Mist applications. PAF Primer must be dry before PAF Vera Mist is applied.

Mixing:

PAF Vera Mist shall be mixed for 1 minute with a mixing blade powered by a 450-500 rpm drill, prior to application of the material. Do not overmix. A small amount of water may be added to adjust workability. Do not add more than 6 oz of water per pail.

Application:

PAF Vera Mist is applied in a single coat process. Apply an even-thin coat using a steel towel, not exceeding 1/8" in thickness. After the coat is applied, lightly float the surface with a plastic trowel. A float may be used to bring out the aggregate to the surface. Float lightly over the finished surface , cleaning the float several times in the process.

Curing:

PAF Vera Mist drying is upon environment conditions. Under average conditions (70°F) PAF Nova Stone will dry in 48 hours. Lower temperature conditions require PAF Vera Mist to be covered or protected for longer periods.

Limitations:

Surface temperatures shall not be below 50°F (10°C). Environment temperature must be between 50°F (10°C) and 90°F (32°C) for PAF Nova Stone applications. Do not use PAF Vera Mist on exposed exterior

horizontal surfaces. Do not apply PAF Vera Mist on surfaces that will receive sealant.

Storage:

PAF Vera Mist should be stored in sealed containers avoiding sunlight and in temperatures above 40°F (4°C).

Technical Testing Data:

Upon request.

Specifications for this product are based on optimal environmental conditions (70°F ambient temperature with 50% humidity) for preparation, mixing, application and curing. Specification parameters may vary as environmental conditions change. Consult the product's Safety Data Sheet or GHS Section located on the product package for hazard identification and first aid measures. **KEEP OUT OF REACH OF CHILDREN.**

Warranty:

Manufacturers or Western Blended Products (WBP) warrants its products to be of merchantable quality and suitable for the general purpose for which they were intended, when applied in accordance with WBP instructions. Manufacturers of WBP do not warrant its products to be suitable for any purpose or use other than for which they were intended. Liability under this warranty is limited to supplying new material without charge, or at manufacturers of WBP option, to a refund of the purchase price. In the event of a claim under this warranty, written notice must be given to the originating plant of the WBP goods at the address shown hereon. This limited warranty is issued and accepted in lieu of all other expressed warranties, and expressly excludes liability for consequential damages. Some states do not allow the exclusion or limitation of incidental or consequential damages, or limitations on how long an implied warranty lasts, so the above limitations and exclusions may not apply to you. This warranty gives you specific legal rights, and you may also have other rights that vary from state to state.

DEC 2017

Sacramento Stucco Co.
1550 Parkway Blvd. West Sacramento, CA 95691 / (916) 372-7442
Western Stucco Co.
6101 N. 53rd. Drive Glendale, AZ 85311 / (623) 939-9455
Rio Grande Stucco Co.
9151 Roseway Drive El Paso, TX 79907 / (915) 858-3494

Visit us on the web:
westernblended.com



Western Blended Products are manufactured in the U.S.A. utilizing the strictest quality control processes to ensure consistent, high-performance products on every project.

